



RSC-210

4.2 VOC EURO URETHANE CLEARCOAT

Technical Data Sheet
Technical Hotline 800.735.0303

PRODUCT#

RSC-210

DESCRIPTION

4.2 VOC EURO URETHANE CLEARCOAT

ACTIVATOR

RSA-218

RSA-219


MEDIUM CLEARCOAT ACTIVATOR

SLOW CLEARCOAT ACTIVATOR



DESCRIPTION

RSC-210 Euro Urethane Clearcoat is a 2:1 European style clearcoat formulated to be economical and easy to use while producing a high gloss finish throughout a wide range of changing shop conditions. RSC-210 provides great value for any application.



MIXING

RSC-210

2 Parts

TO

RSA-218, 219

1 Part



APPLICATION

Apply 2-3 full wet coats at 40-50 psi or (6-10 psi at the gun when using HVLP), allowing a 10-15 minute flash between coats at 77°F.



DRYING AT 77° F.

DUST FREE

TACK FREE

TO DELIVER

TO BUFF

RSA-218

20 MINUTES

20-30 MINUTES

14 - 16 HOURS

16 - 24 HOURS

RSA-219

25 MINUTES

45 MINUTES

14 - 16 HOURS

16 - 24 HOURS



FORCE DRYING

FLASH TIME @ 77° F 15 MINUTES

BAKE TIME @ 140° F 40 MINUTES

Allow a 1 to 2 hour cool-down time before wet sanding or buffing after force drying.

TECHNICAL DATA

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
RSC-210	3.6	427	2.2	268
RSA-218	4.6	554	4.6	554
RSA-219	4.1	492	4.1	492
V.O.C. (RTS):				
RSC-210/RSA-218	4.0	483	3.0	363
RSC-210/RSA-219	3.8	456	2.9	343

Manufacturer's Exclusive Limited Warranty

For Industrial use only by professional, trained personal using proper safety protective equipment. Not for sale to, or use by, the general public. Manufacturer warrants that its products are free from defect in material and workmanship at the time of sale. In the event that any product is proved by objective testing and analysis to have been defective at the time of sale, upon the return of the defective product, the manufacturer shall replace the product at no cost, excluding the shipping costs, as the exclusive remedy.

This warranty does not cover damage caused by accident, misuse, improper application, improper combination of products or tampering. ALL IMPLIED WARRANTIES WHETHER IT BE OF MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. THIS WARRANTY EXCLUDES ALL INCIDENTAL AND CONSEQUENTIAL DAMAGES.

NOTE: Refinish Solutions products are not recommended for use in temperatures below 60° F.

Use below these temperatures will effect dry times and performance.

FOR INDUSTRY USE ONLY

Read MSDS Before Use

Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

SEE MSDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.