



# **RSC-220**

## **EXTRA GLOSS URETHANE CLEARCOAT**

**Technical Data Sheet**  
Technical Hotline 800.735.0303

### **PRODUCT#**

RSC-220

### **DESCRIPTION**

EXTRA GLOSS URETHANE CLEARCOAT

### **ACTIVATOR**

RSA-225

RSA-226

RSA-227

FAST CLEARCOAT ACTIVATOR


MEDIUM CLEARCOAT ACTIVATOR

SLOW CLEARCOAT ACTIVATOR



### **DESCRIPTION**

Extra Gloss Clearcoat is a high gloss, easy to buff durable clearcoat. With an easy 4:1 mix ratio. Extra Gloss Clearcoat sprays easily and flows to a high gloss finish and dries quickly.



### **MIXING**

RSC-220

4 Parts

**TO**

RSA-225, 226, 227

1 Part



### **APPLICATION**

Apply 2-3 full wet coats at 40-50 psi or (6-10 psi at the gun when using HVLP), allowing a 10-15 minute flash between coats at 77°F.



### **DRYING AT 77° F.**

DUST FREE

TACK FREE

TO DELIVER

TO BUFF

### **RSA 225,226**

20 MINUTES

20 - 30 MINUTES

14 - 16 HOURS

16 - 24 HOURS

### **RSA 227**

25 MINUTES

45 MINUTES

14 - 16 HOURS

16 - 24 HOURS



### **FORCE DRYING**

FLASH TIME @ 77° F     15 MINUTES

BAKE TIME @ 140° F     40 MINUTES

Allow a 1 to 2 hour cool-down time before wet sanding or buffing after force drying.

## **TECHNICAL DATA**

V.O.C. as Delivered:	Regulatory VOC in LBS./GAL.	Regulatory VOC in G./L.	Material VOC in LBS./GAL.	Material VOC in G./L.
RSC-220	4.6	546	3.4	404
RSA-225	3.2	382	3.2	382
RSA-226	3.2	382	3.2	382
RSA-227	3.0	365	3.0	365
V.O.C. (RTS):				
RSC-220/RSA-225	4.2	505	3.3	399
RSC-220/RSA-226	4.2	504	3.3	399
RSC-220/RSA-227	4.2	500	3.3	396

**Viscosity:** 17 - 19 Seconds  
**Weight Solids:** 39.94 - 39.98%  
**Film Build:** 0.8 - 1.0 mils  
**Coverage:** 510.1 - 512.4 sq. ft.

### **Manufacturer's Exclusive Limited Warranty**

For Industrial use only by professional, trained personal using proper safety protective equipment. Not for sale to, or use by, the general public. Manufacturer warrants that its products are free from defect in material and workmanship at the time of sale. In the event that any product is proved by objective testing and analysis to have been defective at the time of sale, upon the return of the defective product, the manufacturer shall replace the product at no cost, excluding the shipping costs, as the exclusive remedy.

This warranty does not cover damage caused by accident, misuse, improper application, improper combination of products or tampering. ALL IMPLIED WARRANTIES WHETHER IT BE OF MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE ARE EXCLUDED. THIS WARRANTY EXCLUDES ALL INCIDENTAL AND CONSEQUENTIAL DAMAGES.

**NOTE: Refinish Solutions products are not recommended for use in temperatures below 60° F.**

**Use below these temperatures will effect dry times and performance.**

### **FOR INDUSTRY USE ONLY**

#### **Read MSDS Before Use**

Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions.

The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

**SEE MSDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.**