

### DESCRIPTION:

SW-4100 Universal Clearcoat is two-component acrylic clear coat, provides easy application, easy drying, good leveling and high gloss, suitable for large area refinishing.

### COMPONENTS:

SW-4100	Universal Clearcoat
SW-401	Fast Activator
SW-402	Medium Activator
SW-403	Slow Activator

### SUBSTRATES:


1K Basecoat

### SURFACE PREPARATION:




Remove wax, silicon or other contaminations with 8910 degreaser.

### MIX RATIO:



SW-4100	4 parts
SW-401/402/403	1 part

### POT LIFE:




4 hours with SW-402 @ 74°F

### ADDITIVES:

- Blushing: 8960 Retarder Solvent over 86°F. Refer to tech sheet of Retarder Solvent for details.
- Fisheyes: 8930 Anti Silicon (0.5-1%) in the paint remained and re-spray the affected area.
- Overspray: 8920 Thinner SRA. Refer to tech sheet of Thinner SRA for details.


### APPLICATION:



#### Spray gun set up:

Gravity feed (upper pot):  
1.2-1.5mm 3-5kg/cm<sup>2</sup>  
Siphon feed (below pot):  
1.4-1.7mm 3-5kg/cm<sup>2</sup>

Please refer to gun manufacturer for proper spray pressure recommendations.



Coats: 2-3 coats, 40-60 µm  
Flash off time: wet spray, 3-5 mins. between coats @ 74°F  
Air drying: allow 15-20 mins.

purge time before baking.

### DRY TIME:



@ 68°F  
Dust free: 35 minutes  
Dry to polish: 6 hours

@ 140°F  
Dust free: 10 minutes  
Dry to polish: 30 minutes

### Re-application

If there are particles and runs after spray, sand the affected area with P2000 sandpaper after through drying, then polish to solve the problem.



### CLEARING:

Clean equipment immediately with solvent after application

### Note:

- Shelf Life: 2 years in original sealed can at cool and dry place at 41-95°F.

### PHYSICAL DATA:

VOC: 4.5 lbs/gal

### FOR PROFESSIONAL USE ONLY

#### Read MSDS Before Use

**NOTE:** The information in this data sheet is based on our knowledge and the current laws. It is always the responsibility of the user to fulfill the requirements of local rules and legislations. The uncertain factors may affect the application of products, such as the condition of substrate. We do not accept any liability on loss, damage and performance of products unless we issue a special agreement. Always read the latest Material Data Sheet and the Technical Data sheet before applying the products.