## **Technical Data Sheet**



Distributed in

The United States of America: by Peter Kwasny Inc. 62-64 Enter Lane Islandia, NY 11749 Canada: Peter Kwasny Spraypaint Canada Inc. 40 University Avenue, Suite 904 Toronto, ON. M5J 1T1

Toll free North America
Phone: 1-844-426-6330 / Fax: 1-866-226-6434
order@kwasny.us / service@kwasny.us
www.spraymax.com

SprayMax®

1K Clear Acrylic

319 g NET WT. 11.3 oz

Art. Nr. 3680058



### **Product**

**Description / Purpose**1K clear coat for quick coating and longterm sealing

of repair paint jobs and new paint jobs on cars and

motorcycles.

**Properties** • Easy to use

· Dries quickly

· High gloss level

· No color deviation

· Good weathering resistance

Very good levelling

· Very good polishing ability

Material base Acrylic resins

**Colour** Transparent

Gloss level gloss,

78+ / -4 gloss units at 20° measuring angle

Solid content 20 % per weight

**EPA Coating Category**CCP Clear Coatings Product

PWR Limit 1.50



# CARB Aerosol Rule Coating Category (01/2017)

CC Clear Coatings PWR Limit 0.85

## **Substrate**

Solvent and waterborne base coat systems, old paint coats dried according to manufacturer's instructions (cleaned and sanded).

## **Processing**

**Protection measures** 



Wear personal protection equipment.

(respiratory mask / gloves / goggles)

For more information, see safety data sheet.

Shake



Shake can thoroughly for at least 2 minutes from when the mixing balls are heard.

Spray to test



After shaking the can, test spray and check compatibility with the surface and the colour.

**Spraying distance** 



6 - 8 inches / 15 - 20 cm

**Spray passes** 



Dry film thickness 1.2 - 1.8 mil (30 - 45 μm) (approx. 2 - 3 spray coats)

Flash-off time



Flash time: approx. 5 - 10 min between each spray coat

**Processing conditions** 



Optimum application at 64° F - 77° F (18° C - 25° C) and a relative humidity from 40 - 60 %.

Coverage



approx. 5.4 - 8.1 sq ft (0.5 - 0.75 m²) / aerosol at approx. 1.2 - 1.6 mil (30 - 40  $\mu$ m) dry film thickness



#### **Drying**



dust dry: 10 min

dry to touch: approx. 20 min

Ready for polishing: approx. 12 hours

The stated values refer to the above mentioned processing conditions. The level of dryness is

determined pursuant to DIN 53150.



IR drying possible,
Respect technical manual

#### **Finish**



After painting, turn the can upside down and spray for 3 - 5 seconds to clean the valve.

## **Additional Information**

**Important Information** 



Avoid bumps, friction and impact.

#### **Shelf Life**



60 months

The usage period refers to an unused can that is stored correctly at a temperature of 60° F - 77° F / 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed.

#### **Disposal**



The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

#### Note

For professional use only.

Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved. We reserve the right to update, amend or supplement the content of the information without prior notice.