


TECHNICAL DATA SHEET

C210LV Euro MS Clear 2.1 VOC



SUBSTRATES

This clearcoat can be used over any solvent, or low VOC basecoat.



MIXING



+



2
C210LV
Clearcoat

1
CH2101
or
CH2102
or
CH2103
Hardener

Hardener Selection Chart

CH2101	55°-80°F
CH2102	75°- 90°F
CH2103	90°F and above



APPLICATION

Apply 2-3 full wet coats




RECOAT

Basecoat:

Allow basecoat to dry to touch prior to applying clearcoat

Clearcoat:

C210LV may be repaired and recoated after 16-24 hours or when force dried after 1 hour cool down.



DRYING

Flash Time

10-15 minutes

Dry Time

16-24 hours

Force Dry

40 mins @ 140F



BUFFING

16-24 hours air dry or 1 hour after cool down from baking

**Temperature, humidity and film thickness will affect buff times.



PHYSICAL DATA

Pot Life:

1 -2 hours

If used as instructed, this product is designed to comply with Volatile Organic Compound (VOC) Standards in low-VOC jurisdictions, for Automobile Refinish Coatings. Confirm compliance with state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.

PRODUCT DESCRIPTION:

C210LV is a 2.1 VOC European Style 2:1 mix clearcoat that provides optimum flow and leveling for spot, panel, and overall refinishing. This clearcoat is extremely versatile and may be used over any solvent, or low VOC basecoat.

SURFACE PREPARATION:

1. Allow the final coat of basecoat to dry to touch prior to applying clearcoat.
2. Use a tack cloth to remove any surface contaminants that may have settled on the basecoat.
3. Apply C210LV Euro MS Clear 2.1 VOC

**PERSONAL PROTECTION**

- For use by trained professionals only.
- Read label, directions, and MSDS before use.
- Use appropriate Personal Protective Equipment while mixing and spraying.

REGULATORY DATA

C210LV	As Packaged		As Applied	
	Lb/gal	g/L	Lb/gal	g/L
Actual VOC	1.5 Max	130 Max	1.2 Max	145 Max
Regulatory VOC	2 Max	240 Max	2.1 Max	250 Max
Density	8 – 9	960 – 1080	8 – 10	860 – 1080
	Wt%	Vol%	Wt%	Vol%
Total Solids Content	40 – 45	38 – 43	50 – 55	40 – 45
Total Volatile Content	55 – 60	55 – 60	55 – 60	57 – 63
Water	0	0	0	0
Exempt Compound Content	< 45	< 45	< 47	< 45
Coating Category	Clear Coating			

If used as instructed, this product is designed to comply with Volatile Organic Compound (VOC) Standards in low-VOC jurisdictions, for Automobile Refinish Coatings. Confirm compliance with state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.